



Version: 10 April 2017

AURUNA[®] 570

GOLD SILVER ELECTROLYTE



Alkaline-Cyanide Gold Alloy Electrolyte – Gold-Saving

AURUNA[®] 570 is an alkaline-cyanide alloy electrolyte for depositing green-yellow gold coatings. The gold-silver alloy has a fineness of approx. 18 carats. The coatings are gold-saving, they are bright even as thick layers. For thin layers, a variant with a low gold content is available (AURUNA[®] 570 LC).

The long-term stable AURUNA[®] 570 electrolyte is easy to operate and suitable for rack and barrel. It is used for decorative applications.



Advantages

- Gold-saving 18 carat layers
- Alkaline-cyanide gold alloy electrolyte
- Free of cadmium
- For decorative applications
- Bright even as thick layers
- Easy bath maintenance
- The coatings are RoHS compliant
- Suitable for rack and barrel

Applications

- Jewellery
- Watches
- Spectacle frames
- Writing implements
- Lighting
- Household articles
- Cutlery
- Accessories

AURUNA® 570

GOLD SILVER ELECTROLYTE




TECHNICAL SPECIFICATIONS

Electrolyte characteristics	
Electrolyte type	Alkaline-cyanide
Metal content	8 (7.5 - 8.5) g/l Au 3 (2.5 - 3.5) g/l Ag
pH value	> 11
Operating temperature	35 (30 - 40) °C
Current density range	1.0 (0.2 - 1.8) A/dm ²
Plating speed	Approx. 0.6 µm/min at 1.0 A/dm ²
Anode material	Stainless steel

Coating characteristics	
Coating	Gold-silver
Alloy composition	75 wt. % Au 25 wt. % Ag
Colour of deposit	Green-yellow
Brightness	Bright
Hardness of deposit HV 0.015 (Vickers) approx. values	115 HV
Max. coating thickness	> 10 µm
Density of the coating	Approx. 15.5 g/cm ³

Plating Speed and Plating Rate in Dependence on Current Density



Umicore Galvanotechnik GmbH
Klarenbergstrasse 53-79
73525 Schwaebisch Gmuend (Germany)

Technical Support: Phone +49 7171 607-305
Sales Department: Phone +49 7171 607-204

www.ep.unicore.com


umicore
Electroplating

The information and statements contained herein are based on our experience in the fields of research and applied technology and are believed to be accurate at the time of publication, but - unless agreed in writing - we make no warranty with respect thereto, including but not limited to any results to be obtained. This product information sheet in the English language prevails any translation.