



Version: 30 May 2017

# PALLUNA<sup>®</sup> ACF-100

## PALLADIUM-NICKEL ELECTROLYTE



### High-Speed Deposition for Continuous Lines

The new palladium nickel electrolyte PALLUNA<sup>®</sup> ACF-100 has all the technical advantages of other electrolytes - but without the smell of ammonia. The deposited layers are ductile, crack-free and resistant to abrasion. Furthermore, PALLUNA<sup>®</sup> ACF-100 has the cost benefit on its side: With comparable contact properties to those of hard gold, the palladium-nickel layer is by far the less expensive alternative.

PALLUNA<sup>®</sup> ACF-100 is a high-speed electrolyte, free of ammonia and chloride, for depositing a bright palladium-nickel-alloy in reel-to-reel lines (selective dipping, jet plating, brush plating) and in tabplaters.

Depending on the operation conditions, the electrolyte deposits alloy coatings with approx. 80 % of Pd. The alloy composition is largely independent of the current density. Electrolyte maintenance without ammonia and chloride. Breakdown products could be removed by carbon treatment easily. Continuous carbon treatment is feasible.



### Advantages

- Free from ammonia and chloride
- No smell nuisance by ammonia gas
- Reduced corrosion of equipment
- Long lifetime of anodes
- Ductile coatings
- Constant alloy composition

### Applications

- Electrical contacts for Connector Industry
- Hardgold replacement

# PALLUNA® ACF-100

## PALLADIUM-NICKEL ELECTROLYTE




### TECHNICAL SPECIFICATIONS

Electrolyte characteristics	
Electrolyte type	Free from ammonia and chloride
Metal content	15 g/l Pd, 16 g/l Ni
pH value	5.5 at 60 °C
Operating temperature	60 °C
Current density range	Up to 70 A/dm <sup>2</sup>
Plating speed	Up to 15 µm/min
Anode material	MMO (type PLATINODE® 187 S0)


Coating characteristics	
Coating	Palladium-Nickel
Alloy composition	80 wt.% Pd 20 wt.% Ni
Colour of deposit	White
Brightness	Bright
Hardness of deposit HV 0.015 (Vickers) approx. values	500 - 550 HV
Max. coating thickness	10 µm
Density	10.8 g/cm <sup>3</sup>
Elongation	Approx. 5 %
Bendability (10 mm mandrel)	2 µm crack-free

#### Deposition Speed, Alloy Composition vs. Current Density



PALLUNA® ACF-100  
JetLab4: 15 g/l, 16 g/l Ni; pH 5.5; 60°C; 1.11 g/cm<sup>3</sup>; 800 l/h

#### Crack- and Void-Free Coating



Umicore Galvanotechnik GmbH  
Klarenbergstrasse 53-79  
73525 Schwaebisch Gmuend (Germany)

Technical Support: Phone +49 7171 607-322  
Sales Department: Phone +49 7171 607-204

[www.ep.umicore.com](http://www.ep.umicore.com)

**umicore**  
Electroplating

The information and statements contained herein are based on our experience in the fields of research and applied technology and are believed to be accurate at the time of publication, but - unless agreed in writing - we make no warranty with respect thereto, including but not limited to any results to be obtained. This product information sheet in the English language prevails any translation.