



Version: 30 May 2017

AURUNA[®] 530

GOLD COBALT ELECTROLYTE



Electrolyte for Abrasion-Resistant, Low-Corrosion Hard Gold Layers

AURUNA[®] 530 is a weakly acidic hard gold electrolyte with high current efficiency. Its essential property is its high resistance to abrasion and corrosion.

By choosing advantageous operating conditions (pH-value and temperature), printed circuit boards can be treated in a way which is particularly friendly to resists and lacquers, thus avoiding the lifting of masking materials.

With a gold content of at least 3 g/l, the desired high current efficiency can be reached even with sensitive resists. The plating speed is approx. 0.29 $\mu\text{m}/\text{min}$ at 1 A/dm² and 35 °C.



Advantages

- Weakly acidic hard gold electrolyte based on gold-cobalt with high current efficiency
- Good compatibility with resists, like dry film and soldermask
- Low contact resistance
- High abrasion resistance
- Good thickness distribution
- Easy maintenance and high stability of the electrolyte
- Low-pore layers with good corrosion resistance

Applications

- Contacts on plug-in cards
- Printed circuit boards

AURUNA® 530

GOLD COBALT ELECTROLYTE




TECHNICAL SPECIFICATIONS

Electrolyte characteristics	
Electrolyte type	Weakly acidic
Metal content	4 (3 - 6) g/l Au
pH value	4.0 (4.0 - 4.4)
Operating temperature	35 °C
Current density range	0.8 A/dm ²
Plating speed	0.1 - 0.5 µm/min
Anode material	Pt-Ti (type PLATINODE® Pt/Ti)


Coating characteristics	
Coating	Gold-cobalt
Alloy composition	99.7 wt.% Au 0.3 wt.% Co
Colour of deposit	Yellow
Brightness	Semi-bright
Layer hardness HV 0.015 (Vickers)	approx. 170 HV
Density of the coating	Approx. 18 g/cm ³

Corrosion Resistance Test AURUNA® 530

Before test



After test



NAV-Test, 1 h, 25 °C on production board. No pin holes found.

Umicore Galvanotechnik GmbH
Klarenbergstrasse 53-79
73525 Schwaebisch Gmuend (Germany)

Technical Support: Phone +49 7171 607-357
Sales Department: Phone +49 7171 607-204

www.ep.umicore.com


umicore
Electroplating

The information and statements contained herein are based on our experience in the fields of research and applied technology and are believed to be accurate at the time of publication, but - unless agreed in writing - we make no warranty with respect thereto, including but not limited to any results to be obtained. This product information sheet in the English language prevails any translation.