



Version: 16 July 2018

PALLUNA[®] ACF-800

PURE PALLADIUM ELECTROLYTE



Ammonia-Free and Chloride-Free

PALLUNA[®] ACF-800 is a newly developed neutral pure palladium electrolyte, which has a wide operating range and can be plated directly on nickel, copper or copper alloys.

PALLUNA[®] ACF-800 is ammonia-free and thereby avoids unpleasant smells. Furthermore the lifetime of the anodes is significantly extended and the corrosion of the system is immensely reduced by abstaining from the use of chloride. The produced layers are ultra-bright, crack-free and show low internal stress. At the same time they are ductile and extremely corrosion resistant.

By continuous activated carbon treatment organic decomposition products in the electrolyte can be removed.



Advantages

- No unpleasant smell of ammonia
- Easy electrolyte maintenance
- High plating speed
- Neutral, ammonia-free and chloride-free electrolyte
- Ductile, ultra-bright and crack-free coatings
- Very good soldering and bonding features
- For rack and reel-to-reel operation

Applications

- Printed circuit boards
- Contacts on plug-in cards
- Smartcards
- On bonding wire

PALLUNA[®] ACF-800

PURE PALLADIUM ELECTROLYTE



TECHNICAL SPECIFICATIONS

Electrolyte characteristics	
Electrolyte type	Free from ammonia and chloride
Metal content	12 (5 - 30) g/l Pd
pH value	6.5
Operating temperature	55 - 65 °C
Current density range	Up to 25 A/dm ²
Plating speed	Up to 4 µm/min at 20 A/dm ²
Anode material	MMO (type PLATINODE [®] 187 S0)

Coating characteristics	
Coating	Pure palladium
Purity	99.9 wt.% Pd
Colour of deposit	White / light and bright
Brightness	Bright
Hardness of deposit HV 0.015 (Vickers) approx. values	Approx. 280 HV
Coating density	Approx. 12 g/cm ³
Corrosion resistance	Good

YOUR CONTACT

Do you have a specific question or would you like a no-obligation quote calculation? Our specialist will be happy to help you with any technical questions you might have.



Markus Legeler
Manager Sales International

Mail: markus.legeler@eu.umicore.com
Phone: +49 (0) 7171 607 - 204

